



gloveon Celeste

Nitrile Exam Gloves Powder Free, Standard Cuff

GloveOn® Celeste is a popular choice from our nitrile exam glove range. With high tensile strength and resistance to chemicals, GloveOn Celeste's superior tactility commends it to delicate procedures.



Physical Dimensions		
Length (mm)	≥ 230	
Palm Thickness (Centre of Palm) (mm)	0.07 ± 0.02	
Finger Thickness (13mm ± 3mm from tip) (mm)	0.10 ± 0.02	
Physical Properties		
Before Ageing	After Ageing	
Tensile Strength (MPa)	≥ 18	≥ 16
Elongation (%)	≥ 500	≥ 400
Performance Requirements		
Inspection Level	AQL	
Watertightness	G1	1.5
Physical Dimensions	S2	4.0
Physical Properties	S2	4.0
Visual Inspection (Major)	S4	2.5
Visual Inspection (Minor)	S4	4.0
Particulate Residue	N = 5	≤ 2mg/glove

REORDER CODE

CLS121XS	X-SMALL
CLS121SS	SMALL
CLS121MM	MEDIUM
CLS121LL	LARGE
CLS121XL	X-LARGE

FEATURES

- Fingertip textured • Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested • Ambidextrous
- Standard cuff • Violet blue colour

PACKAGING

200 gloves per box for XS to L
180 gloves per box for XL
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 407779, FDA 510(k), EU 10/2011, MDR (EU) 2017/745, REACH, EU 2016/425, ROHS DIRECTIVE 2011/65/EU, EC 1935/2004

STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124, ASTM D6978, ASTM F1671, EN 16523-1, EN 420, EN ISO 374 part 1 (Type B) & 5, EN 374 part 2 & 4, EN 455 part 1, 2, 3 & 4, EN 1186, EN 13130, EN 421 (excluding Clause 4.3), CEN/TS 14234, HACCP International Certified, ISO 10993 part 5 & 10

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978 - Test Report PN120750)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	10.2 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Tosopar), 20.0mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	30.2 Minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Celeste nitrile glove at 10.2 minutes and 30.2 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Chemical	EN 16523-1 Permeation Level	EN 374-4 Mean Degradation (%)
K 40% Sodium Hydroxide	6	-25.7
P 30% Hydrogen Peroxide	2	44.8
T 37% Formaldehyde	5	-17.1

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Product disclaimer - <https://munglobal.com/product-disclaimer/>

A brand by



Mun Australia
Toll free: 1800 456 837
munglobal.com.au

