



## Latex Exam Gloves Powder Free, Standard Cuff

GloveOn® Innova is our light weight powder free latex glove, with a unique fully textured surface for better grip in both wet and dry environments. These versatile gloves come with high tensile strength and superb barrier protection properties, which are suitable for any demanding task in any market segment.



Tested in accordance with  
EN ISO 374-5:2016  
Resistance to Bacteria and Fungi - pass  
Resistance to Viruses - pass

### Physical Dimensions

Length (mm)  $\geq 230$

Palm Thickness (mm)  $0.11 \pm 0.03$

Finger Thickness (mm)  $0.13 \pm 0.03$

### Physical Properties

Tensile Strength (MPa)

$\geq 18$

$\geq 16$

Elongation (%)

$\geq 650$

$\geq 500$

### Performance Requirements

#### Inspection Level

#### AQL

Watertightness

G1

1.5

Physical Dimensions

S2

4.0

Physical Properties

S2

4.0

Visual Inspection (Major)

S4

2.5

Visual Inspection (Minor)

S4

4.0

Particulate Residue

N = 5

$\leq 2\text{mg/glove}$

Protein Content

N = 3

$\leq 50\mu\text{g/g}$

\*Full test reports on Sensitisation Testing, Primary Skin Irritation and Residual Proteins Testing are available upon request.

### REORDER CODE

INV211XS X-SMALL

INV211SS SMALL

INV211MM MEDIUM

INV211LL LARGE

INV211XL X-LARGE

### FEATURES

- Fully textured
- Powder free
- Made with natural rubber latex
- Protein level  $\leq 50\mu\text{g/g}$
- Lab chemical tested
- Ambidextrous
- Standard cuff
- Natural colour

### PACKAGING

100 gloves per box

10 boxes per carton

### REGULATORY COMPLIANCE

ARTG 408965, FDA 510(k), REACH, MDR (EU) 2017/745, EU 10/2011, RoHS Directive 2011/65/EU, EC 1935/2004, EU 2016/425

### STANDARDS

ASTM F1671, ASTM D5151, ASTM D6124, ASTM D3578, ASTM D5712, EN 455 part 1, 2, 3 & 4, EN ISO 374-1 (Type B), EN 16523-1, EN 374 part 2, 4 & 5, EN 420, EN 1186, EN 13130, CEN/TS 14234, ISO 10993 part 5 & 10, HACCP Certified

### MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Measured breakthrough time (minutes)	>10	>30	>60	>120	>240	>480
Permeation performance level	1	2	3	4	5	6

Chemical	EN 16523-1:2015 Permeation Level	EN 374-4:2013 Mean Degradation (%)
K 40% Sodium Hydroxide	3	-24.7
P 30% Hydrogen Peroxide	4	19.8
T 37% Formaldehyde	5	-23.1