

gloveon Matador

Nitrile Exam Gloves Powder Free, Long Cuff



GloveOn® Matador is built with quality, consistency and reliability in an 8.0mil nitrile glove. With GloveOn® Matador, users can take confidence in wearing a stronger glove to shape their performance in their work duties.



Physical Dimensions	
Length (mm)	290 ± 10
Palm Thickness (Centre of Palm) (mm)	0.20 ± 0.04
Finger Thickness (13mm ± 3mm from tip) (mm)	0.28 ± 0.04
Cuff Thickness (25mm from bead) (mm)	0.14 ± 0.04
Physical Properties	
Tensile Strength (MPa)	Before Ageing: ≥ 18, After Ageing: ≥ 16
Elongation (%)	Before Ageing: ≥ 500, After Ageing: ≥ 400
Performance Requirements	
	Inspection Level: G1, AQL: 1.5
Watertightness	G1, 1.5
Physical Dimensions	S2, 4.0
Physical Properties	S2, 4.0
Visual Inspection (Major)	S4, 2.5
Visual Inspection (Minor)	S4, 4.0
Particulate Residue	N = 5, ≤ 2mg/glove

REORDER CODE

MTR151SS	SMALL
MTR151MM	MEDIUM
MTR151LL	LARGE
MTR151XL	X-LARGE

FEATURES

- Fingertip textured • Powder free
- Not made with natural rubber latex
- Chemo drugs tested
- Lab chemical tested • Ambidextrous
- Long cuff • Sky blue colour

PACKAGING

50 gloves per box for S to XL
10 boxes per carton

REGULATORY COMPLIANCE

ARTG 407779, FDA 510(k), REACH,
MDR 2017/745, EU 2016/425,
RoHS Directive 2011/65/EU

STANDARDS

ASTM D6319, ASTM D5151, ASTM D6124,
ASTM D6978, ASTM F1671, EN ISO 21420,
EN 16523-1, EN 455 part 1, 2, 3 & 4,
EN ISO 374 part 1 (Type A), 2, 4 & 5,
ISO 11193-1, ISO 10993 part 5 & 10,
HACCP International Certified

MANUFACTURING ACCREDITATIONS

ISO 9001, ISO 13485, EN ISO 13485

Chemotherapy Drugs and Concentration (Tested for Resistance to Permeation by Chemotherapy Drugs as per ASTM D6978 - Test Report PN 107200B)	Minimum Breakthrough Detection Time (minutes)
Carmustine (BCNU), 3.3mg/ml (3,300 ppm)	90.6 minutes
Cisplatin, 1.0mg/ml (1,000 ppm)	>240 minutes
Cyclophosphamide (Cytoxan), 20.0mg/ml (20,000 ppm)	>240 minutes
Dacarbazine (DTIC), 10.0mg/ml (10,000 ppm)	>240 minutes
Doxorubicin Hydrochloride, 2.0mg/ml (2,000 ppm)	>240 minutes
Etoposide (Toposar), 20.00mg/ml (20,000 ppm)	>240 minutes
Fluorouracil, 50.0mg/ml (50,000 ppm)	>240 minutes
Methotrexate, 25.0mg/ml (25,000 ppm)	>240 minutes
Mitomycin C, 0.5mg/ml (500 ppm)	>240 minutes
Paclitaxel (Taxol), 6.0mg/ml (6,000 ppm)	>240 minutes
Thiotepa, 10.0mg/ml (10,000 ppm)	165.8 minutes
Vincristine Sulfate, 1.0mg/ml (1,000 ppm)	>240 minutes

WARNING: Carmustine and Thiotepa, at the tested concentration, degraded Matador nitrile glove at 90.6 minutes and 165.8 minutes, respectively. The safe use of gloves in chemotherapy treatment is solely the decision of clinicians authorised to make such decision.

Chemical	EN 16523-1 Permeation Level	EN ISO 374-4 Mean Degradation (%)	Measured breakthrough time (minutes)					
			>10	>30	>60	>120	>240	>480
J n-Heptane	3	36.5	1	2	3	4	5	6
K 40% Sodium Hydroxide	6	-1.8						
L 96% Sulphuric Acid	2	100.0						
O 25% Ammonium Hydroxide	2	46.9						
P 30% Hydrogen Peroxide	6	20.4						
T 37% Formaldehyde	6	22.3						
S 40% Hydrofluoric Acid	2	n/a						

Product disclaimer - <https://munglobal.com/product-disclaimer/>

A brand by



Mun Australia
Toll free: 1800 456 837
munglobal.com.au



Proud Supporter of
Birthing Kit Foundation (Australia)

